



INDUSTRIAL ENTERPRISES (Pvt) LTD

6-N, INDUSTRIAL AREA, GULBERG II, LAHORE, PAKISTAN

TEL: 042-35712229, 35752229, FAX: 042-35713119, E-mail: info@thermopore.com

TECHNICAL DATA SHEET FOR THERMOPORE® EXPANDED POLYSTYRENE [EPS] INSULATION SHEETS - 35KG/M³ DENSITY

Property	Test	Unit	Value
Nominal Density (minimum)	ASTM C303	Kg/m ³	35
Thermal Resistance [R-value per inch]	ASTM C578	(hr.ft ² .°F)/BTU	5.50
U-Value [per inch]	ASTM C578	BTU/(hr.ft ² .°F)	0.180
Thermal Conductivity [k-value]	ASTM C578	W/m.K	0.027
Compressive Strength [10% deformation]	ASTM D1621	Psi	30-32
Flexural Strength [minimum]	ASTM C203	Psi	75
Water Absorption [maximum]	ASTM C272	% of volume	<2.0%
Water Vapour Permeance	ASTM E96	Perm. 1 inch	<1.0%
Dimensional Stability	ASTM D2126	%	2%
Fire Rating (if FR Grade)	ASTM E84	-	Class A
Flame Spread (if FR Grade)	ASTM E84	mm	<20
Smoke Index developed (if FR Grade)	ASTM E84	-	150-300

THERMOPORE® , THERMOPORE-BLUE®, THERMOSPRAY® and THERMOBOARD® are our registered trademarks

Head Office: 6-N Gulberg II, Industrial Area, Lahore. Tel: 042-35712229, 042-35752229 Fax: 042-35713119 Mobile: 0335 8444000

Islamabad Office: Off. # 5, 3rd Floor, Capital Plaza, G11 Markaz, Islamabad. Tel: 051-229 0436 Mobile: 0335 8444111

Faisalabad Office: Mobile: 0335 8444222